

## WELD CUSH 20 VISOKO KVALITETNA ZAŠČITNA BLAZINA ZA VARJENJE

## Tehnični list

<b>Tkanina ALF</b>				
tkanje	plain	500 gr/m <sup>2</sup>		
debelina	mm	0.7		
temperaturna odpornost	C	1390 C		
Vsebnost				
70 / 30	%	Al <sub>2</sub> O <sub>3</sub> / SiO <sub>2</sub>		
<b>SILIKA mat</b>				
gostota	kg/m <sup>3</sup>	150		
debelina	mm	12 mm		
vsebnost	%	94- 96 SiO <sub>2</sub>		
temperaturna odpornost	C	1000		
Certifikati		ISO 1887		
Module B building		No.114.563		
Toplotna prevodnost	W/mK	850 C 0,19		
<b>Tkanina glass aluminizirana</b>				
tkanje	plain	300 gr/m <sup>2</sup>		
Debelina	mm	0,25		
sestava		E glass / alu		
Temperaturna odpornost	C	550		
Alu folija	micron	20		
<b>CARBO oksid akrilon. karbon vlakna</b>				
teža	gr/m <sup>2</sup>	200		
debelina	mm	5		
pretržna sila	N/5cm	90		
prepustnost zraka	l/m <sup>2</sup> /s 200pa	1400		
sestava				
karbon	%	62		
dušik	%	21.5		
kisik	%	12		
el upornost	Ohms cm	8 x 10 <sup>8</sup>		
test vnetljivosti kisik index		ISO 4589, ASTM 2863		
LOI index	%	40+		
velikost vlaken	micron	12.5		
<b>Tkanina glass silikonizirana</b>				
tkanje	Cr. twill	470 gr/m <sup>2</sup>		
debelina	mm	0,4		
sestava		E glass / silikon		
Temperaturna odpornost tkanine		500 C		
Temperaturna odpornost silikon premaza		250 C		
<b>SUKANEC</b>				
		aramid		
<b>ROBNI TRAK</b>				
		fiberglass 0.18		

